

FORMABILITY

SUGGESTED MINIMUM BEND RADIUS: LONGITUDINAL BENDS

GRADE	< 6	6 TO 12	12 TO 25	25 TO 40	25 TO 40
230G	1t	1t	2t	3t	4t
350G	2 1/2t	3 1/2t	--	--	--
400G	3t	5t	--	--	--
260W	1 1/2t	1 1/2t	2t	3t	--
(A36)	1 1/2t	2t	3t	4t	--
300W	2 1/2t	2 1/2t	4t	--	--
(44W)	3 1/2t	3 1/2t	4t	--	--
350W	5t	5t	--	--	--
(HSS)					
400W					
480W					
260WT	1 1/2t	2t	3t	3t	4t
300WT	1 1/2t	2t	3t	4t	5t
350WT	2 1/2t	3t	4t	--	--
400WT	3 1/2t	3 1/2t	6t	--	--
480WT	4t	5t	6t	--	--
350R	2t	3t	--	--	--
350A	2t	3t	5t	--	--
400A	3t	4t	5t	--	--
480A	4t	5t	6t	--	--